

20. (Amended) The process according to claim 14, wherein the cobalt compound which is loaded on the aluminum-coated ceramic sheet comprises particles with a size of 1 nm to 100 nm.

21. (Amended) The process according to claim 14, wherein the cobalt compound is loaded by impregnation, dipping, a sol-gel process or a reverse micelle process.

22. (Amended) The process according to claim 14, wherein the calcining temperature is between 300 and 800°C.

23. (Amended) The process according to claim 13, wherein the ceramic sheet is a porous ceramic sheet.

24. (Amended) The process according to claim 13, wherein the ceramic sheet is made of silica-alumina.

25. (Amended) The process according to claim 13, wherein the ceramic sheet is heated to dry before aluminum is deposited.

26. (Amended) The process according to claim 14, wherein aluminum is deposited by vacuum deposition, electrochemical deposition or sputtering.

27. (Amended) The process according to claim 1, wherein the carbon compound is at least one member of the group consisting of saturated hydrocarbon compounds, unsaturated

BEST AVAILABLE COPY

hydrocarbon compounds, aromatic hydrocarbon compounds and oxygen-containing hydrocarbon compounds.

a3

28. (Amended) The process according to claim 27, wherein the reaction temperature for the step of decomposing the carbon compound is between 400 and 1100°C.

Please add claims 29-31 as follows.

29. (New) The process according to claim 14, wherein the ceramic sheet is a porous ceramic sheet.

30. (New) The process according to claim 14, wherein the ceramic sheet is made of silica-alumina.

31. (New) The process according to claim 14, wherein the ceramic sheet is heated to dry before aluminum is deposited.

REMARKS

The above amendments eliminate multiple dependency in the claims.

Respectfully submitted,



David S. Abrams
Reg. No. 22,576

Roylance, Abrams, Berdo & Goodman, L.L.P.
1300 19th Street, N.W., Suite 600
Washington, DC 20036
(202)659-9076

Dated: 2/4/02

BEST AVAILABLE COPY